

Mn-Zn 功率铁氧体材料特性

Mn-Zn Power Ferrite Characteristics

特性 Characteristics	符号 Symbol	单位 Unit	测定条件 Conditions	JNP57
初始磁导率 Initial permeability	μ_i	-	25°C	4000±25%
饱和磁通密度 Saturation Magnetic Flux Density	B_s	mT	25°C H=1194A/m, f=50Hz	430
			100°C H=1194A/m, f=50Hz	270
剩磁 Residual Magnetic Flux Density	B_r	mT	25°C	-
矫顽力 Coercive Force	H_c	A/m	25°C	14
功率损耗 Power Loss	P_v	mw/cm ³	25°C $f=100\text{KHz}, B=200\text{mT}$	-
			100°C $f=100\text{KHz}, B=200\text{mT}$	-
居里温度 Curie Temperature	T_c	°C	-	≥140
电阻率 Electrical Resistivity	ρ	$\Omega \cdot m$	25°C	3
密度 Density	d	g/cm ³	-	4.9

注：以上数据是根据标准样环T25X15X8获得的典型数据，有关产品的具体性能会在此基础上有所调整。

The above typical data are calculated from the standard toroid core. The specific property of any parts will be adjusted a little based on these date.

JNP57 材料特性曲线
JNP57 Material Characteristics Curve

