

Mn-Zn 功率铁氧体材料特性

Mn-Zn Power Ferrite Characteristics

特性 Characteristics	符号 Symbol	单位 Unit	测试条件 Conditions	JNP96
初始磁导率 Initial Permeability	μ_i	-	25°C	3300±25%
饱和磁通密度 Saturation Magnetic Flux Density	B_s	mT	25°C H=1194A/m,f=50Hz	530
			100°C H=1194A/m,f=50Hz	410
剩磁 Residual Magnetic Flux Density	B_r	mT	25°C	85
矫顽力 Coercive Force	H_c	A/m	25°C	9
功率损耗 Power Loss	P_{cv}	mW/cm ³	25°C $f=100kHz, B=200mT$	320
			80°C $f=100kHz, B=200mT$	270
			100°C $f=100kHz, B=200mT$	290
			120°C $f=100kHz, B=200mT$	330
			140°C $f=100kHz, B=200mT$	380
居里温度 Curie Temperature	T_c	°C	-	≥ 220
电阻率 Electrical Resistivity	ρ	$\Omega \cdot m$	25°C	7
密度 Density	d	g/cm ³	-	4.85

注：以上数据是根据标准样环T25X15X8获得的典型数据，有关产品的具体性能会在此基础上有所调整。

The above typical data are calculated from the standard toroid core. The specific property of any parts will be adjusted a little based on these date.

